

**PA6-GF15**

15% glass fiber reinforced

Mechanical Properties	Typical data (dry)	Unit	Test method
Stress at break	125	MPa	ISO 527
Strain at break	3,5	%	ISO 527
Tensile Modulus	6000	MPa	ISO 527
Flexural strength	170	MPa	ISO 178
Flexural modulus	5200	MPa	ISO 178
Charpy Impact strength (+23°C)	45	kJ/m <sup>2</sup>	ISO 179
Charpy notched Impact strength (+23°C)	7	kJ/m <sup>2</sup>	ISO 179
Charpy impact strength (-30°C)	40	kJ/m <sup>2</sup>	ISO 179
Charpy notched Impact strength (-30°C)	6	kJ/m <sup>2</sup>	ISO 179

  

Thermal Properties	Typical data	Unit	Test method
Melting temperature, 10°C/min	220	°C	ISO 11357
Temp. of deflection under load (1.80 MPa)	195	°C	ISO 75
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75
CTE, linear, Parallel to Flow	0.3	E-4/°C	ISO 11359-1,-2
CTE, linear, Transverse to Flow	0.8	E-4/°C	ISO 11359-1,-2

  

Electrical Properties	Typical data	Unit	Test method
CTI Tracking index	600 (cond)	-	IEC 60112
Surface resistivity	10 <sup>14</sup> (cond)	Ohm	IEC 60093
Volume resistivity	10 <sup>13</sup>	Ohm*m	IEC 60093

  

Physical Properties	Typical data	Unit	Test method
Density	1230	kg/m <sup>3</sup>	ISO 1183
Moisture absorption at Equilibrium	2.3	%	ISO 62
Water absorption at Saturation	7.6	%	ISO 62
Linear mold shrinkage, Flow	0.32	%	ISO 294-4
Linear mold shrinkage, Transverse	0.96	%	ISO 294-4

  

Flammability	Typical data	Unit	Test method
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Glow Wire Flammability Index	700	°C	IEC 60695-2-12

Disclaimer: Unless specified to the contrary, the value given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum value. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and the coloring.

# Volgamid® B1G3



KuibyshevAzot  
PUBLIC JOINT-STOCK COMPANY

## PA6-GF15

15% glass fiber reinforced

### Processing Properties

Injection molding temperature	245-275	°C
Mold temperature	50-80	°C
Drying temperature	80	°C
Drying time	4-8	H
Moisture content before processing	<0,15	%

### Characteristics

Designed for the production of injection molding of various products and parts in the automotive, machinery, household appliances and other industries

Disclaimer: Unless specified to the contrary, the value given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum value. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and the coloring.

Novozavodskaya str.6, 445007, Togliatti, Samara region, Russian Federation, e-mail: ep@kuazot.ru, website: www.kuazot.ru

Honesty • Consistency • Competence